

CRS-3P

| PROPERTIES | MIN | MAX |
|-----------------------------|-------------|------------|
| Viscosity SFS @ 25°C | 100 | 400 |
| Settlement 5 days, % (a) | | 5 |
| Storage Stability 1 day (b) | | 1 |
| Particle charge | Positive(c) | |
| Sieve % | | 0.10 |

TESTS ON RESIDUE FROM DISTILLATION

| | | |
|-----------------------------------|------|-----|
| Residue by 177°C Distillation, % | 65.0 | |
| Penetration @ 25°C | 90 | 150 |
| Elastic Recovery% @ 25° C | 50 | |
| Elastic Recovery% @ 10° C | 58 | |
| Solubility in Trichlorethylene, % | 97.5 | |

- (a) The test requirement for settlement may be waived when the emulsified asphalt is used in less than 5 days, or the purchaser may require that the settlement test be run from the time the sample is received until it is used, if the elapsed time is less than 5 days.
- (b) The 24-hour (1 day) storage stability test may be used instead of the 5 day settlement test.
- (c) Must meet a pH requirement of 6.7 maximum (AASHTO T 200 pH of Aqueous Solutions with the Glass Electrode) if the Particle charge test result is inconclusive.