

Crushed Screening Percent Passing						
	¾"-½"	⅝"-No. 4	½"-No. 4	⅜"-No. 4	⅜"-No. 10	No. 4-0
1"	100	---	---		---	---
¾"	95-100	100	---		---	---
⅝"	---	95-100	100		---	---
½"	0-20	---	90-100	100	100	---
⅜"	0-5	---	60-85	70-90	90-100	100
No. 4	---	0-10	0-3	0-5	0-20	76-100
No. 10	---	0-3			0-5	30-60
No. 200	0-1.5	0-1.5	0-1.5	0-1.5	0-1.5	0-10.0
% fracture, by weight, min.	90	90	90	90	90	90

All percentages are by weight.

The fracture requirement shall be at least one fractured face and will apply to the combined aggregate retained on the No. 4 sieve in accordance with FOP for AASHTO TP 61.

The finished product shall be clean, uniform in quality, and free from wood, bark, roots, and other deleterious materials.

Crushed screenings shall be substantially free from adherent coatings. The presence of a thin, firmly adhering film of weathered rock shall not be considered as coating unless it exists on more than 50 percent of the surface area of any size between successive laboratory sieves.

The portion of aggregate for bituminous surface treatment retained on a No. 4 sieve shall not contain more than 0.1 percent deleterious materials by weight.

Fine aggregate used for choke stone applications meeting the grading requirements of [Section 9-03.1\(2\)B](#) may be substituted for the No. 4-0 gradation.

9-03.5 Vacant

9-03.6 Aggregates for Asphalt Treated Base (ATB)

9-03.6(1) General Requirements

Aggregates for asphalt treated base shall be manufactured from ledge rock, talus, or gravel, in accordance with the provisions of [Section 3-01](#), that meet the following test requirements:

Los Angeles Wear, 500 Rev.	30% max.
Degradation Factor	15 min.

9-03.6(2) Grading

Aggregates for asphalt treated base shall meet the following requirements for grading:

Sieve Size	Percent Passing
2"	100
½"	56-100
No. 4	32-72
No. 10	22-57
No. 40	8-32
No. 200	2.0-9.0

All percentages are by weight.