



Tel: (360) 816-8540
Toll Free: (800) 888-5048
Fax: (360) 816-8541
asphalt@albina.com
www.albina.com

801 Main Street
Vancouver WA 98660

HFMS-2/HFE-150

PROPERTIES	MIN	MAX
Viscosity SFS @ 25°C	100	
Storage Stability 1 day		1
Sieve %		0.10**
Residue by 260°C Distillation, %	65	
Oil distillate by volume of emulsion %		7
TESTS ON RESIDUE FROM DISTILLATION		
Penetration @ 25°C, dmm	100	300*
Float Test at 60°C, sec	1200	
Ductility @ 25°C, cm.		40

* Modification of AASHTO M-140

** AASHTO a 0.30% is acceptable for samples taken at point of use.

11/06/2018